

Hempel's Wax TecCel

Product characteristics

Description

Hempel's Wax TecCel is a premium high performance liquid wax with TecCel technology providing UV protection, long lasting, deep gloss finish with excellent durability.

Recommended use

For use on gelcoat, painted and varnished surfaces after polishing with Hempel's Custom Marine Polish.

Suitable for both manual and machine use

Features

- Forms a long lasting hard wax surface. Leaves an easy to clean, water repellent surface with long-lasting protection.

Product safety

Flash point 61°C [142°F]

VOC content

| Legislation | Value |
|-------------|--------------------------|
| EU | 222 g/L [1.85 lb/US gal] |

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

Product data

Product code

69034

Standard shade / code

- 98880

Volume solids

15 ± 2%

Specific gravity

1 kg/L [8 lb/US gal]

Surface preparation

Cleanliness

- Clean with Hempel's Pre-Clean or Hempel's Boat Shampoo.

Maintenance and Repair

- Deteriorated surfaces: Renew gloss and colour with Hempel's Rubbing Liquid.

Application

Application method

Shake well before use. Do not apply in direct sunlight.

Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

Application remarks

- Apply the product with a clean, dry, soft cloth.
- Treat only small areas at a time. Allow the surface to dry 5-10 minutes.
- Polish with a clean cloth or a polishing machine to obtain a high gloss finish.
- Change to clean cloths frequently.

Hempel's Wax TecCel

Drying and overcoating

Product compatibility

- Previous coat: Recommended products are: Hempel's Rubbing Liquid, Hempel's Custom Marine Polish

Drying time

Allow freshly painted surfaces to dry/cure for at least 90 days before applying the product.

Other remarks

- Later, if repainting is required, it is very important to remove all traces of wax by using Hempel's Pre-Clean.

Storage

Shelf life

| | |
|----------------------------|-----------------------|
| Ambient temperature | 25°C [77°F] |
| Product | 60 months |

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. For advice, please consult Hempel.

Storage conditions

- Temperature must not go below 0°C [32°F] during transport and storage.

Additional documents

Additional information is available at the Hempel website <https://www.hempel.com/service-and-support/technical-guidelines> or at your local Hempel website:

- Explanatory Notes for Product Data Sheet.
- Application methods.
- Further information: Hempel Yacht Paint Manual and hempelyacht.com

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

| No. | Document description | Location/comments |
|-----|--|---|
| 1. | Technical Statement | One-off specific advice provided on request for specific projects |
| 2. | Specification | Only issued for specific projects |
| 3. | PDS | This document |
| 4. | Explanatory Notes to the PDS | Available at www.hempel.com and contain relevant information about the Product testing parameters |
| 5. | Application Instruction | Where available, at www.hempel.com |
| 6. | Generic technical guidelines (e.g. on application and surface preparation) | Where available, at www.hempel.com |

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.